

Interference of exciton-polariton waves in GaSe nanocrystals

<https://doi.org/10.1016/j.mtcomm.2021.102355>

V.V.Zalamai ^{a b}

I.G.Stamov ^c

N.N.Syrbu ^a

a

Laboratory of Optical Spectroscopy and Optical Communications, Technical University of Moldova, 168 Stefan cel Mare Avenue, 2004, Chisinau, Republic of Moldova

b

National Center for Materials Study and Testing, Technical University of Moldova, Bv. Stefan cel Mare 168, Chisinau, 2004, Republic of Moldova

c

T.G. Shevchenko State University of Pridnestrovia, 25 Oktyabrya Street 107, 3300, Tiraspol, Republic of Moldova

Abstract

Absorption, reflection, photoluminescence and wavelength modulation transmission spectra of GaSe single crystals were investigated in temperature range 300 – 10 K. From fitting of contours of excitonic reflection spectra parameters of excitons as energy of transversal exciton $\omega_0 = 2.1212$ eV, longitudinal transversal splitting $\omega_{LT} = 2.3$ meV, effective mass $M = 2.5m_0$, background permittivity $\epsilon_b = 5.2$ and damping constant $\gamma = 1.4$ were determined. Effective masses of electrons ($m_{c1} = 0.37m_0$) and holes ($m_{v1} = 2.13m_0$) in the Brillouin zone center were estimated. An interference of waves of upper and lower branches of exciton-polaritons was found out in wavelength modulation transmission spectra of GaSe nanocrystals.